



# PRODUCT DATA SHEET

## DRYLOK® LATEX BASE MASONRY WATERPROOFER

### DESCRIPTION

Latex Base DRYLOK Masonry Waterproofer is the easy and manageable way to deal with water seepage problems. Formulated for waterproofing all interior, exterior, above or below grade masonry walls, cinder and concrete blocks, stucco and brick, retaining walls, basement walls and foundations. Latex Base DRYLOK has been tested to ASTM D-7088 Resistance to Hydrostatic Pressure and ASTM D-6904 Resistance to Wind Driven Rain.

### GUARANTEED

Guaranteed to Stop Water - up to 10 psi according to test. That's greater than a column of water 22 feet high! Latex Base DRYLOK is backed by a 10-year product warranty.

### WARRANTY

Latex Base DRYLOK Masonry Waterproofer, when applied according to directions on a properly prepared bare masonry surface, is warranted to provide a waterproof coating for ten (10) years from date of sale, warranty includes subsequent owners, or we will refund the cost of the DRYLOK. This is the exclusive remedy. Excludes leaks due to cracking of the surface, recurring efflorescence and application over surfaces previously coated with a paint other than DRYLOK Masonry Waterproofer.

### SURFACE PREP

May be applied on slightly damp surfaces, but best results are obtained when applied over dry surfaces. For best waterproofing results, wait for a dry (rain-free) period. Surface must be clean and free from dirt, dust, grease, oil, form release compound or paint. Patch all holes or cracks and the floor/wall joint with DRYLOK Fast Plug or a fast setting hydraulic cement, and smooth the patch evenly with the surface around it. DRYLOK Etch (liquid or powder formula) or muriatic acid, used according to manufacturer's directions, are effective efflorescence removal agents. May be applied over previous coatings in sound condition but the warranty is void. Not recommended for use on horizontal surfaces subject to foot traffic. Old paint in poor condition must be removed by wire-brushing, sand blasting or by using other suitable means.

### APPLICATION

STIR THOROUGHLY BEFORE AND DURING APPLICATION. DO NOT THIN. Paint only when air and surface temperatures are 50°F or higher. Apply Latex Base DRYLOK Masonry Waterproofer directly on bare masonry. For best waterproofing results, wait for a dry (rain-free) period before application. Apply first coat with DRYLOK BRUSH or good quality nylon bristle brush working the WATERPROOFER into the pores of the masonry - avoid excessive brushing (see COVERAGE). APPLY TWO COATS. Allow to dry 3 hours between coats. The second coat may be applied by brush, roller or spray. For information on spray application, write UGL and ask for Spray Specification Sheet D-88.

### WARNING

If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

### IMPORTANT

If leaking is still present after two coats, it indicates that pores or pinholes are still open. These areas should be painted again. When painting the inside of concrete fish ponds or birdbaths, allow Latex Base DRYLOK Masonry Waterproofer to dry at least one week before filling with water.

If desired, a high quality latex paint can be applied over DRYLOK after 24 hours for decorative purposes.

### COVERAGE

On rough, porous masonry, apply at the rate of 75 sq. ft. per gallon for the first coat and up to 125 sq. ft. per gallon for succeeding coats. On dense, smooth surfaces, apply at the rate of 100-125 sq. ft. per gallon for the first coat and up to 125 sq. ft. per gallon for succeeding coats.

PRODUCT DATA  
DRYLOK LATEX BASE MASONRY WATERPROOFER

# DRYLOK® LATEX BASE MASONRY WATERPROOFER

## TINTING

Maybe tinted to light shades with alkali-proof universal tinting colors. Use only 25% of color normally recommended. Do not use more than 2 fl. oz. of colorant per gallon.

## CAUTION

Cancer hazard: Contains Crystalline Silica, which can cause cancer. Risk of cancer depends on duration and level of exposure to dust generated from sanding surfaces. Use only with adequate ventilation. Do not breathe spray mist or dust. Vapor harmful. May affect the brain or nervous system causing dizziness, headache or nausea. Causes eye, nose and throat irritation. May be harmful if absorbed through skin. Harmful if swallowed. NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Avoid exposure to dust by wearing an appropriate (NIOSH approved) particulate respirator during sanding. Follow respirator manufacturer's directions for respirator use. Close container after each use. Do not get in eyes, on skin or clothing. Wash thoroughly after handling. This product contains a chemical known to the State of California to cause cancer.

## AVAILABILITY

Latex Base DRYLOK Masonry Waterproofer is available in white in one-gallon, two-gallon and five-gallon containers. Gray, beige and blue are available in one-gallon cans and five-gallon pails. It may be purchased at hardware stores, home centers, paint stores and lumberyards.

## CLEAN-UP

Clean application tools immediately after use in warm, soapy water.

## FIRST AID

If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. In case of contact, immediately flush eyes with plenty of water for at least 15 minutes. Get medical attention immediately. If swallowed, do not induce vomiting. Get medical attention immediately. KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY. KEEP FROM FREEZING. For additional health and safety information please refer to the "Material Safety Data Sheet". Latex Base DRYLOK Masonry Waterproofer meets all environmental standards for low emissions of solvent vapors.

## TECHNICAL DATA

### Viscosity

120 to 130 Ku

### pH

9.5 to 9.9

### % Solids by Weight

66 to 68

### % Solids by Volume

48 to 50

### Coverage

75 to 125 ft.<sup>2</sup>/Gallon/Coat

### Recommended film thickness/coat

13 to 21 wet mils

### Dry time (to touch)\*

30 minutes to 1 hour

### Dry time (to recoat)\*

3 hours

### Dry time (to apply decorative latex paint)\*

24 hours

### VOC Content

<100 g/L

\*Dry time is dependent upon temperature and humidity. Apply when temperature is between 50° and 90° F and relative humidity is below 60%.

LR908



United Gilsonite Laboratories  
Corporate Headquarters  
1396 Jefferson Avenue  
Dunmore, PA 18509  
Tel: 1-800-272-3235  
www.ugl.com